

IN THE CLAIMS:

1-52. (Cancelled)

53. (Currently Amended) A ~~solid~~ carbon product comprising C₆₀ in a macroscopic amount prepared by the process comprising:

- (a) vaporizing a carbon source in the presence of an inert quenching gas under conditions effective to provide a sooty carbon product comprising C₆₀ molecules;
- (b) depositing the sooty carbon product on a collecting substrate;
- (c) removing the sooty carbon product from the collecting substrate;
- (d) contacting the sooty carbon product with a non-polar organic solvent effective to dissolve C₆₀ molecules, said solvent being present in an amount effective to dissolve the C₆₀ molecules in said sooty carbon product; and
- (e) recovering from said resulting product formed when the sooty carbon product was contacted with said solvent a solid carbon product comprising C₆₀ in a macroscopic amount.

54. (Currently Amended) The ~~solid~~ carbon product of Claim 53 in which the carbon in step (a) is vaporized in an evacuated reactor.

55. (Currently Amended) The ~~solid~~ carbon product of Claim 54 in which the carbon source of step (a) is vaporized in an evacuated bell jar.

56. (Currently Amended) The ~~solid~~ carbon product of Claim 53 in which the carbon source subject to vaporization in step (a) is graphite.

57. (Currently Amended) The ~~solid~~ carbon product of Claim 53 in which the carbon source subject to vaporization in step (a) is graphite rods.

58. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the carbon source is vaporized in step (a) through heating the carbon source by means of an electrical current of sufficient intensity to produce the sooty carbon product.

59. (Currently Amended) The ~~solid~~ carbon product of Claim 58 wherein the electrical current is about 100 amps.

60. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the inert quenching gas of step (a) is a noble gas.

61. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the carbon source is vaporized in step (a) at a pressure ranging from 50 torr to 400 torr.

62. (Currently Amended) The ~~solid~~ carbon product of Claim 61 wherein the carbon is vaporized in step (a) at approximately 100 torr.

63. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the carbon is vaporized in step (a) at a pressure ranging from about 2 to 3 atmospheres.

64. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the collecting substrate

in step (b) is a glass surface.

65. (Currently Amended) The ~~solid~~ carbon product of Claim 60 wherein the inert gas is helium or argon.

66. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein the non-polar organic solvent of step (d) is carbon disulfide, benzene, carbon tetrachloride or toluene.

67. (Currently Amended) The ~~solid~~ carbon product of Claim 66 wherein the solvent is benzene.

68. (Currently Amended) The ~~solid~~ carbon product of Claim 66 wherein the solvent is carbon tetrachloride.

69. (Currently Amended) The ~~solid~~ carbon product of Claim 53 wherein recovery step (e) comprises evaporating the solvent.

70. (Currently Amended) The ~~solid~~ carbon product of Claim 53 further comprising C₇₀.

71. (Currently Amended) The ~~solid~~ carbon product of Claim 53 further comprising:

(f) purifying the carbon product of step (e) to obtain C₆₀.

72. (Currently Amended) The ~~solid~~ product of Claim 71 wherein the purification of step (f) is sublimation at 300-400°C, ~~fractional crystallization, column~~ chromatography, capillary

electrophoresis, ~~HPLC, preparative thin layer chromatography~~, crystallization or extraction.

73. (Previously Presented) A formed or molded product comprising crystalline C₆₀.

74. (Cancelled)

75. (Previously Presented) A free flowing particulate comprised of crystalline C₆₀.

76.-79. (Cancelled)

80. (Previously Presented) A formed or molded product comprising solid C₇₀.

81. (Previously Presented) A free-flowing particulate comprising solid C₇₀.

82.-83. (Cancelled)

84. (Previously Presented) Substantially pure C₆₀.

85. (Previously Presented) Substantially pure solid C₆₀.

86. (Previously Presented) C₆₀ in a macroscopic amount.

87.-88. (Cancelled)

89. (Previously Presented) Substantially pure C₇₀.
90. (Previously Presented) Substantially pure solid C₇₀.
91. (Cancelled)
92. (Previously Presented) Crystalline C₆₀.
93. (Previously Presented) Crystalline C₇₀.
94. (Previously Presented) Substantially pure crystalline C₆₀.
95. (Previously Presented) Substantially pure crystalline C₇₀.
96. (Previously Presented) C₇₀ in a macroscopic amount.
- 97.-101. (Cancelled)
102. (Previously Presented) A macroscopic amount of substantially pure C₆₀.
103. (Previously Presented) A macroscopic amount of substantially pure C₇₀.

104. (Previously Presented) A formed or molded product comprising C₇₀, said C₇₀ being present in a macroscopic amount.

105. (Previously Presented) A free flowing particulate comprising C₇₀, said C₇₀ being present in a macroscopic amount.

106. (Previously Presented) A formed or molded product comprising C₆₀, said C₆₀ being present in a macroscopic amount.

107. (Previously Presented) A free flowing particulate comprising C₆₀, said C₆₀ being present in a macroscopic amount.

108.-110. (Cancelled)

111. (Previously Presented) A solid comprising C₆₀, said C₆₀ being present in a macroscopic amount.

112. (Previously Presented) A solid comprising C₇₀, said C₇₀ being present in a macroscopic amount.

113. (Previously Presented) A sooty product comprising C₆₀, the C₆₀ in said sooty product being present in sufficient concentration to allow a macroscopic amount of said C₆₀ to be separated therefrom.

114. (Previously Presented) A sooty product comprising C_{70} , the C_{70} in said sooty product being present in sufficient concentration to allow a macroscopic amount of said C_{70} to be separated therefrom.

115.-118. (Cancelled)

119. (Previously Presented) A sooty carbon product prepared by the process comprising:

(a) vaporizing a carbon source in the presence of an inert gas to provide a vapor of carbon atoms,

(b) quenching said vapor of carbon in said inert gas under conditions effective to nucleate and condense said vapor of carbon atoms into a sooty carbon product comprising C_{60} molecules, said C_{60} molecules being present in said sooty carbon in sufficient concentrations to allow a macroscopic amount of C_{60} to be separated from said soot.

120.-121. (Cancelled)

122. (Previously Presented) The sooty carbon product of Claim 113, additionally comprising C_{70} .

123. (Previously Presented) The sooty carbon product of Claim 119 additionally comprising C_{70} .

124. (Previously Presented) The sooty carbon product of Claim 119 in which the carbon source

subject to vaporization in step (a) is graphite or amorphous or glassy carbon.

125. (Previously Presented) The sooty carbon product of Claim 119 in which the carbon source subject to vaporization in step (a) is graphite.

126. (Previously Presented) The sooty carbon product of Claim 119 in which the carbon source subject to vaporization in step (a) is graphite rods.

127. (Previously Presented) The sooty carbon product of Claim 119 in which the carbon source in step (a) is vaporized in an evacuated reactor.

128. (Previously Presented) The sooty carbon product of Claim 119 in which the carbon source in step (a) is vaporized in an evacuated bell jar.

129. (Previously Presented) The sooty carbon product of Claim 119 in which the inert gas is a noble gas.

130. (Previously Presented) The sooty carbon product of Claim 129 in which the noble gas is helium or argon.

131. (Previously Presented) The sooty carbon product of Claim 119 in which the process is conducted at a pressure sufficient to nucleate said carbon vapor.

132. (Previously Presented) The sooty carbon product of Claim 131 in which the pressure ranges from 60 torr to 400 torr.

133.-140. (Cancelled)

141. (Currently Amended) A ~~solid~~ carbon product comprised of macroscopic amounts of C₆₀ prepared by the process comprising:

(a) evaporating a carbon source in the presence of an inert quenching gas under conditions effective to produce a sooty carbon product containing C₆₀, said C₆₀ being present in said sooty carbon product in sufficient concentration to allow a macroscopic amount of said C₆₀ to be separated from said sooty product;

(b) collecting the sooty carbon product produced therefrom;

(c) subliming the carbon product comprising a macroscopic amount of C₆₀ from the sooty carbon product; and

(d) condensing the sublimed carbon product comprising a macroscopic amount of C₆₀.

142. (Currently Amended) The ~~solid~~ carbon product of Claim 141 wherein the sublimation occurs at a temperature ranging from 300°-400°C.

143. (Currently Amended) The ~~solid~~ carbon product of Claim 142 wherein step (c) comprises heating the carbon product comprising C₆₀ in a vacuum or inert atmosphere at effective sublimation temperatures to extract the carbon product comprising C₆₀ from said sooty carbon

product.

144. (Currently Amended) The ~~solid~~ carbon product of Claim 141 in which the carbon source in step (a) is vaporized in an evacuated reactor.

145. (Currently Amended) The ~~solid~~ carbon product of Claim 144 in which the carbon in step (a) is vaporized in an evacuated bell jar.

146. (Currently Amended) The ~~solid~~ carbon product of Claim 141 in which the carbon subject to vaporization in step (a) is graphite.

147. (Currently Amended) The ~~solid~~ carbon product of Claim 141 in which the carbon subject to vaporization in step (a) is graphite rods.

148. (Currently Amended) The ~~solid~~ carbon product of Claim 141, wherein the carbon source in step (a) is vaporized by passing an electric current of sufficient intensity to produce a sooty carbon product.

149. (Currently Amended) The ~~solid~~ carbon product of Claim 148, wherein the electrical current is about 100 amps.

150. (Currently Amended) The ~~solid~~ carbon product of Claim 141, wherein the inert quenching gas of step (a) is a noble gas.

151. (Currently Amended) The ~~solid~~ carbon product of Claim 141, wherein the carbon source in step (a) is vaporized at a pressure ranging from 50 torr to 400 torr.

152. (Currently Amended) The ~~solid~~ carbon product of Claim 151, wherein the carbon source is vaporized in step (a) at approximately 100 torr.

153. (Currently Amended) The ~~solid~~ carbon product of Claim 53, wherein the collecting substrate in step (b) is a glass surface.

154. (Currently Amended) The ~~solid~~ carbon product of Claim 150, wherein the noble gas is helium or argon.

155. (Currently Amended) The ~~solid~~ carbon product of Claim 141, wherein C₇₀ is additionally present.

156. (Currently Amended) The ~~solid~~ carbon product of Claim 155, wherein C₇₀ is separated from C₆₀ by ~~sublimation, column~~ sublimation chromatography, fractional crystallization, capillary electrophoresis, HPLC, ~~preparative thin layer chromatography~~, or extraction.

157. (Currently Amended) The ~~solid~~ carbon product of Claim 155, wherein the C₇₀ is separated from C₆₀ by sublimation.

158.-161. (Cancelled)

162. (Currently Amended) The ~~solid~~ carbon product according to Claim 155, wherein the C₇₀ is present in a macroscopic amount.

163.-164. (Cancelled)

165. (Previously Presented) A solid comprising a macroscopic amount of crystalline C₆₀.

166. (Previously Presented) A solid comprising a macroscopic amount of crystalline C₇₀.

167. (Previously Presented) A carbon product comprising a macroscopic amount of solid C₆₀.

168. (Previously Presented) A carbon product comprising a macroscopic amount of solid C₇₀.

169. (Previously Presented) The carbon product of Claim 167, wherein the solid C₆₀ is crystalline C₆₀.

170. (Previously Presented) The carbon product of Claim 168, wherein the solid C₇₀ is crystalline C₇₀.

171.-180. (Cancelled)